

# Product datasheet

## Gjøco Klarlakk Oljebasert



Gjøco Klarlakk Oil-based is an extra bright varnish based on urethane alkyd. Provides a hard and durable surface that is easy to keep clean. Contains light filters that reduce yellowing of the wood. Gjøco Clear Varnish Oil-based is used on spruce and pine floors, parquet, doors, windows, furniture, panels, moldings, etc. Can also be used for wooden boats, etc.

Revised 03.12.2024

Symbols



### Technical data


Type:	Urethane alkyd-based varnish
Gloss:	Silk matt 18-25, semi-matt 55-65, glossy 88-95
Specific gravity:	0.89 kg/l
Solid content:	Ca. 51 volum%
Application method:	Paint brush or short-haired roller.
Thinner/ cleaning agent:	White Spirit
Recommended spreading rate:	12-15 m <sup>2</sup> /litre, depending on the substrate.
Drying times (23 °C, 50 % R.H.):	
Dry to use:	8 hours
Interval between coats:	10 hours. Full adhesion is achieved after 4 weeks of thorough curing. Varies with changes in temperature, humidity, ventilation and film thickness.
Minimum application temperature:	+5 °C. Best results are achieved at room temperature.

### Pretreatment

The substrate is first washed with Gjøco Gulv og Panelrens or Gjøco Husvask to remove grease, soap residue and wax. It is important that the floor is completely clean to ensure adhesion to the new varnish. Previously varnished surfaces and parquet varnished from the factory should be sanded to a matt finish with sandpaper, vacuumed and wiped with a lint-free cloth. It is advisable to use a mop with a microfibre cloth or dry disposable cloths. Be especially careful along edges, moldings and stud joints. Using a sander/disc machine ensures even and thorough sanding. If the previous varnish/oil type is unknown, do a test coat after the floor has been cleaned to check that drying and adhesion are good.

### Directions for use

Stir well before and during use; this is important to avoid streaks. On new, untreated wood, 2-3 coats of Gjøco Klarlakk Oil-based are recommended.

	Previously varnished surfaces 1-2 coats. Cork, porous and extra absorbent surfaces apply a minimum of 5 coats. On untreated wood, thin the first coat with 10-20% Gjøco White Spirit. Sand away any raised fibers with fine sandpaper. Carefully remove sanding dust before applying the next coats undiluted. Light matt sanding is recommended between each coat to ensure good adhesion.
<b>Storage</b>	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Disposal of waste</b>	Liquid varnish should not be emptied into sewers or into nature, but delivered to an approved hazardous waste collection point. Empty, clean and dry packaging should be delivered to an environmental waste disposal station. 
<b>Other information</b>	Different batch numbers are mixed before use to avoid differences in gloss. Thick coats and low temperatures extend the drying time. Avoid exposing the paint to heavy loads (water spills, pressure, etc.) in the first week after painting. Wait at least 3-4 days before placing heavy furniture etc. on the painted surface, and 1 week before laying carpets. Mortar (MS joint) in ship floors can affect the drying time of the paint. Take a sample coat. Package sizes: 0.75 and 3 liters
<b>Safety</b>	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (cat. A/i): 500 g/l (2010). This product contains: <500 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information**

**Gjøco AS**  
 Ørvegen 1160, 6639 Torvikbukt  
 Telephone: +47 712 91 700  
 E-mail: [office@gjoco.no](mailto:office@gjoco.no)

